

## Material: Polytetrafluorethylen

Stand 05/2020

### Short description of material

A high crystalline fluoropolymer with excellent sliding properties, an anti-adhesive surface, the best insulating properties and an almost universal chemical resistance. Disadvantages are its low mechanical strength and high specific weight.

### Application examples

- Bearings
- Bushings
- Shaft seals
- Piston rings
- Insulators
- Thread guides

### Colours

natural

### Mechanical values

#### ISO / EN / DIN

#### Dry

#### Humid

Density	ISO 1183	2,18	--	g/cm <sup>3</sup>
Yield stress	ISO 527	25	--	MPa
Elongation at break	ISO 527	380	--	%
Modulus of elasticity from tensile test	ISO 527	750	--	MPa
Modulus of elasticity from bending test	ISO 178	540	--	MPa
Flexural Strength	ISO 178	6	--	MPa
Impact strength <sup>1)</sup>	ISO 179	without break	without break	KJ/m <sup>2</sup>
Notched-bar Impact Strength	ISO 179	16	--	KJ/m <sup>2</sup>
Ball indentation hardness H358/30	ISO 2039-1	30	--	MPa
Creep rate stress at 1% Dehnung <sup>2)</sup>	DIN EN ISO 899-1	1,5	--	MPa
Sliding friction coefficient against steel (dry running) <sup>3)</sup>	-	0,08	--	-
Sliding wear against steel (dry running) <sup>3)</sup>	-	21,0	--	µm/km

### Thermal values

Melting temperature	ISO 3146	+327	--	°C
Thermal conductivity	DIN EN 12939	0,23	--	W/(K*m)
Specific thermal capacity	-	1	--	J/(g*K)
Coefficient of thermal expansion (linear) <sup>4)</sup>	-	18-20	--	10 <sup>-5</sup> *K <sup>-1</sup>
Operating temperature range (long-term) <sup>5)</sup>	-	-200 bis +260	--	°C
Operating temperature range (short-term) <sup>5)</sup>	-	+280	--	°C
Fire behaviour	UL 94, IEC 60695	V-0	--	-

### Electrical values

Dielectric constant <sup>6)</sup>	IEC 60250	2,1	--	-
Dielectric loss factor <sup>6)</sup>	IEC 60250	0,0005	--	-
Specific volume resistance	IEC 60093	10 <sup>18</sup>	--	Ω *cm
Surface resistance	IEC 60093	10 <sup>17</sup>	--	Ω
Dielectric strength	IEC 60243	40	--	kV/mm
Creep current resistance	IEC 60112	CTI 600	--	-

### Miscellaneous data

Moisture absorption in normal climate until saturated	DIN EN ISO 62	0,01	--	%
Water absorption until saturated	DIN EN ISO 62	<0,01	--	%

<sup>1)</sup> measured with a pendulum impact testing machine 0,1 DIN 51 222

<sup>2)</sup> tension resulting in 1% total elongation after 1.000h

<sup>3)</sup> against steel, hardened and ground

P = 0,05 Mpa; V = 0,6m/s; t = 60 °C near running surface

<sup>4)</sup> For a temperature range of + 23 °C up to + 60 °C

<sup>5)</sup> Experience values established with finished parts that are not under any stress in heated air, depending on the type and form of heat exposure, short-term = max. 1h, long-term=months

<sup>6)</sup> at 10<sup>6</sup> Hz

The content of this datasheet are meant to give an overview of the product's properties. It reflects our current knowledge and may not be complete. The values should be taken as guide values because they are very depend on surrounding conditions and machining methods. The values are in no way a legally binding assurance of the product's properties or its suitability for use in a specific application. All stated values are average values established from many individual tests. They are based on a temperature of 23°C and 50% RH. For specific applications, we recommend determining suitability by means of a trial.

**Managing Director: Dr. Otto Lose**

Phone: +49 2683 977-0

Fax: +49 2683 977-111

[info@licharz.com](mailto:info@licharz.com)

VAT-No.DE 260268077

Licharz GmbH  
Industriepark Nord 13  
53567 Buchholz  
Germany

[www.licharz.com](http://www.licharz.com)